

W I N D S O R I I

Content	Nylon Fiber Matrix
Width	54 inch/137 cm
Weight	8.8 oz/sq yd, 300 g/m ²
Thickness	28 mils; 0.7 mm
Cleanability Code	S/W
Wear	100,000+ double rubs Wyzenbeek Wire screen (ASTM D-4157- 82) *
Crock	Wet 5/Dry 5 (AATCC-8-1988)
Trap Tear Strength	30 lbs. x 30 lbs. (ASTM D-1117-80)
Grab Tensile Strength	100 lbs. x 100 lbs. (ASTM D-5034-90)
Seam Strength	100 lbs. x 100 lbs. (ASTM D-1683-90A)
Colorfastness: Gas Fumes	(AATCC-23, 3 cycles) Class 4-5/Little to no color change
Colorfastness: I	Fadeometer Test (AATCC-16A-90, 100 hrs.) Class 5/ No color change
Colorfastness: II	NA
Flammability Class I	UFAC/NFPA 260-1989
Flammability Pass	California Technical Bulletin 117-2013 Section E – Pass
Flammability Class A Rated	Tunnel Test: (ASTM E84) **
Flame Compatibility	Furniture upholstered with Windsor II and constructed with other suitable components can comply with Cal 133. Can also be treated to meet many international flammability codes.

*Failure in Wyzenbeek abrasion was defined as wear to expose the microfiber.

**Tested as NYTEK with sheeting backing by adhered method.

MAJILITE

1530 Broadway Road, Dracut, Massachusetts 01826-2830, U.S.A. | +1 978 441-6800 | www.majilite.com